

GEOTEXTILE NON-WOVEN 385G/M² 5.25X100M NW32



Characteristics

Characteristic	Value	Norm
Article code	19441	
Commercial Code	GE0385	
Raw material	Polypropyleen	
Colour	White	
Weight (g/m ²)	385	EN ISO 9864
Width (m)	5,25	
Length (m)	100	
Tensile strength MD (kN/m)	32	EN ISO 10319
Tensile strength CD (kN/m)	32	EN ISO 10319
Elongation at max. load MD (%)	50	EN ISO 10319
Elongation at max. load CD (%)	60	EN ISO 10319
Static perforation resistance CBR (N)	5400	EN ISO 12236
Water vapour permeability (l/m ² *sec)	40	EN ISO 11058
Resistance to dynamic perforation (mm)	10	EN ISO 13433
Water flow in plane at 20 kPa (m ² /s)	4x10-6	EN ISO 12958
Thickness at 2 kPa (mm)	2,20	EN ISO 9863-1
Mesh size (µm)	65	EN ISO 12956
Density (kg/dm ³)	0.91	
Melting point (°C)	165	
Certificate	BENOR	

