


GEOTEXTILE WOVEN SG29/29 5.25X100M BENOR 170G/M²



Characteristics

Characteristic	Value	Norm
Article code	20900	
Commercial Code	GE02929	
Raw material	Polypropyleen	
Weight (g/m ²)	170	
Width (m)	5,25	
Length (m)	100	
Tensile strength MD (kN/m)	29	EN ISO 10319
Tensile strength CD (kN/m)	29	EN ISO 10319
Elongation at max. load MD (%)	26	EN ISO 10319
Elongation at max. load CD (%)	26	EN ISO 10319
Static perforation resistance CBR (N)	4100	EN ISO 12236
Sand permeability O90 (µm)	330	EN ISO 12956
Water vapour permeability (l/m ² *sec)	23	EN ISO 11058
Resistance to dynamic perforation (mm)	11	EN ISO 13433
Thickness at 2 kPa (mm)	1	EN ISO 9863-1
Certificate	BENOR	

