


GEOTEXTILE WOVEN SG40/40 5.25X100M BENOR 185G



Characteristics

Characteristic	Value	Norm
Article code	20901	
Commercial Code	GEO4040F	
Raw material	Polypropyleen	
Weight (g/m ²)	185	
Width (m)	5,25	
Length (m)	100	
Tensile strength MD (kN/m)	40	EN ISO 10319
Tensile strength CD (kN/m)	40	EN ISO 10319
Elongation at max. load MD (%)	17.5	EN ISO 10319
Elongation at max. load CD (%)	14	EN ISO 10319
Static perforation resistance CBR (N)	5000	EN ISO 12236
Water vapour permeability (l/m ² *sec)	25	EN ISO 11058
Resistance to dynamic perforation (mm)	12	EN ISO 13433
Thickness at 2 kPa (mm)	1	EN ISO 9863-1
Mesh size (µm)	350	EN ISO 12956
Density (kg/dm ³)	0.91	
Melting point (°C)	165	
Certificate	BENOR	

