



Characteristics

Characteristic	Value	Norm
Article code	63692	
Commercial Code	SUVATAPDET	
Raw material	PE	
Width (mm)	60	
Length (m)	25	
Thickness (mm)	0,34	DIN EN 1942
Tensile strength (N/25mm)	50	DIN EN ISO 29864
Elongation at break MD (%)	20%	DIN EN ISO 29864
Adhesion (N/25mm)	30	DIN EN ISO 29862
Tempature resistance	-40 +80° C	

