

## Superuno V3 T/MEC vapour barrier 3mm 10m<sup>2</sup>



### Description

Superuno V3 is used as a vapour barrier or underlay in multi-layer torch-applied bituminous roofing systems. It is suitable for fully torch-applied installation or loose-laid, ballasted applications. Superuno is a V3 roofing membrane manufactured from APP-modified bitumen with a glass fibre reinforcement. The upper surface is finished with a sand coating, while the underside is provided with a burn-off polyethylene film.

### Characteristics

| Characteristic               | Value               | Norm       |
|------------------------------|---------------------|------------|
| Raw material                 | APP                 |            |
| Length (m)                   | 10                  |            |
| Width (m)                    | 1                   |            |
| Thickness (mm)               | 3                   |            |
| Tensile strength MD (N/50mm) | 350                 | EN 12311-1 |
| Tensile strength CD (N/50mm) | 200                 | EN 12311-1 |
| Elongation at break MD (%)   | 20                  | EN 12311-1 |
| Elongation at break CD (%)   | 20                  | EN 12311-1 |
| Application                  | Fully torch-applied |            |
| Finish                       | Sand                |            |

