

HAND ROLES

LLDPE cast stretch film for manual use.

Characteristic	Method	Unit	Direction	12µm	15µm	17µm	18µm	19µm	20µm	23µm	30µm	35µm	Tolerances
Impact resistance	ASTM D1709 A	g	-	49	50	58	60	65	65	72	85	91	10%
Tensile strength at break	ASTM D882 B	MPa	Machine	26	27	29	29	30	32	27	32	33	10%
			Transversal	16	17	18	17	17	17	20	22	22	10%
Tensile strength at yield	ASTM D882 B	MPa	Machine	5.5	6	6	6	6	6	6	7	7	10%
			Transversal	4.5	5	5	5	5	5	5	6	6.5	10%
Elongation at break	ASTM D882 B	%	Machine	330	360	380	390	400	410	450	500	570	10%
			Transversal	480	500	510	520	520	540	550	600	610	10%
Tear Resistance	ASTM D1922	mN	Machine	1000	1100	1200	1270	1380	1450	1560	1860	2100	10%
			Transversal	1950	2050	2156	2190	2225	2300	2450	2650	2850	10%
Guaranteed Stretch	internal	%	-	50	70	80	90	95	100	115	145	160	5%
Cling	internal	g	-	135	135	135	130	130	130	130	125	120	10%

In case of coloured stretch film these values should be reduced by 10%.

In case of additives these values should be reduced by 5%.

Available:

- Coloured
- Slippery
- AUV 6/12 months
- UV Absorber
- Antistatic
- NetRoll
- OxoRoll
- Cling Out/In/Both
- Printed

The above values are to be considered as indicative in order to facilitate the choice and usage, but are not given for guarantee purposes.

www.deschacht.eu

Riolering
& Afvoer

Dak, Gevel
& Isolatie

Folies

Oostakker | Antwerpsesteenweg 1068, 9041 Gent-Oostakker | T +32 (0)9 355 74 54 | F +32 (0)9 355 76 79 | oostakker@deschacht.eu
Aartselaar T +32 (0)3 870 69 69 | **Tielt** T +32 (0)51 68 93 77 | **Geel** T +32 (0)14 56 38 30
Zedelgem T +32 (0)50 27 61 11 | **Hamme** T +32 (0)52 25 87 20 | **Hoogstraten** T +32 (0)3 340 20 60