

STANDARD

LLDPE cast stretch film for general applications. To be used only on wrapping machines WITHOUT prestretch group.

Characteristic	Method	Unit	Direction	12µm	15µm	17µm	20µm	23µm	30µm	35µm	Tolerances
Impact resistance	ASTM D1709 A	g	-	40	50	70	75	85	100	125	10%
Tensile strength at break	ASTM D882 B	MPa	Machine	22	27	30	32	32	33	35	10%
			Transversal	17	17	18	18	20	22	22	10%
Tensile strength at yield	ASTM D882 B	MPa	Machine	6	6,5	6,5	6,5	6,5	7	7	10%
			Transversal	4,5	5	5	5	5,5	6	6,5	10%
Elongation at break	ASTM D882 B	%	Machine	400	420	430	460	480	550	600	10%
			Transversal	500	550	570	600	650	670	680	10%
Tear Resistance	ASTM D1922	mN	Machine	1600	1700	2100	2200	2500	2700	3000	10%
			Transversal	2300	2350	2712	3200	3220	3300	3300	10%
Guaranteed Stretch	internal	%	-	60	70	90	110	145	170	180	5%
Cling	internal	%	-	135	135	135	130	130	125	120	10%

In case of coloured stretch film these values should be reduced by 10%.

In case of additives these values should be reduced by 5%.

Available:

- Coloured
- Slippery
- AUV 6/12 months
- UV Absorber
- Antistatic
- NetRoll
- OxoRoll
- Cling Out/In/Both
- Printed

The above values are to be considered as indicative in order to facilitate the choice and usage, but are not given for guarantee purposes.

www.deschacht.eu

Riolering
& Afvoer

Dak, Gevel
& Isolatie

Folies

Oostakker | Antwerpsesteenweg 1068, 9041 Gent-Oostakker | T +32 (0)9 355 74 54 | F +32 (0)9 355 76 79 | oostakker@deschacht.eu
Aartselaar T +32 (0)3 870 69 69 | **Tielt** T +32 (0)51 68 93 77 | **Geel** T +32 (0)14 56 38 30
Zedelgem T +32 (0)50 27 61 11 | **Hamme** T +32 (0)52 25 87 20 | **Hoogstraten** T +32 (0)3 340 20 60