

### LDPE FILM - FILM GREEN OPAQUE 0.40 6M

<b>Reference</b>	Deschacht Product: PE blown - coex			
<b>Dimensions</b>	Width 6000mm	tolerance +10%/-10%mm		
	Thickness 0,20mm	Tolerance +/- 30%		
<b>Material</b>	Film based on LDPE regeneration			
<b>Optical</b>	Color: multicolor, resultant, predominance of shades of green Print: /			
<b>Physical</b>	Density: 0,924kg/m <sup>3</sup> + 10%/-10% UV resistance: non			
<b>Mechanical</b>	Stress at break	MD	9MPa	PN-EN ISO 527-1:2012(E) PN-EN ISO 527-3:1998
		TD	7MPa	
	Tensile strength	MD	6N/15mm	
		TD	5N/15mm	
	Stress at yield	MD	6MPa	
		TD	5MPa	
	Yield strength	MD	5N/15mm	
		TD	4N/15mm	
% Elongation at break	MD	n.e.		
	TD	n.e.		
Shrinking	MD	n.e.	DIN 55 543 (at 135°C±2°C, 10s.)	
	TD	n.e.		
<b>Packing</b>	Core type: 76mm Core thickness: n.e. Pallet: n.e.			

Afmetingen, kleur en gewichten zijn ter indicatieve titel en onder voorbehoud van wijzigingen.  
Dimensions, couleurs et poids sont à titre indicatif et sous réserve de modification.

[www.deschacht.eu](http://www.deschacht.eu)

Riolering  
& Afvoer

Dak, Gevel  
& Isolatie

Folies

Oostakker | Antwerpsesteenweg 1068, 9041 Gent-Oostakker | T +32 (0)9 355 74 54 | F +32 (0)9 355 76 79 | oostakker@deschacht.eu  
 Aartselaar T +32 (0)3 870 69 69 | Tiel T +32 (0)51 68 93 77 | Geel T +32 (0)14 56 38 30  
 Zedelgem T +32 (0)50 27 61 11 | Hamme T +32 (0)52 25 87 20 | Hoogstraten T +32 (0)3 340 20 60